

# Product Data Sheet

## Pad Printing Ink

**Coates Screen Inks**  
Screen and Pad Printing Inks

# TP 218/GL

## Solvent Based Pad Printing Ink Range, 2-Component

### APPLICATION

Pad printing inks for printing on glass, ceramics, duroplastics, metals as well as chromium and nickel-plated, gold-plated or rhodium coated surfaces.

### PROPERTIES

- Pad inks TP 218/GL are solvent based pad printing inks. They are processed as 2-component ink with hardener.
- Ink range TP 218/GL shows good printability. The inks dry chemical-physically and result in a glossy finish.
- TP 218/GL inks are suitable for a variety of applications, especially for technical applications and cosmetic articles requiring high resistances.
- Cured prints exhibit high mechanical resistances as well as good chemical resistances against many organic solvents, thinned alkalis and acids, oils and grease.
- Due to the binders (epoxy resin) pad printing inks TP 218/GL are suitable for indoor and short-term outdoor applications.
- We offer three different hardeners to optimally adjust TP 218/GL inks to various requirements.
- Note: Because of the variety of substrates, pre-tests are essential. It is also advised to check efficiency of possibly required pre-treatment of substrates (cleaning/degreasing, flame/corona/plasma treatment) or maybe even post-treatment (flame-drying).

### COLOUR SHADES - OVERVIEW

- Mixing System: C-MIX 2000 12 colour shades for mixing of RAL, PMS and HKS colours.
- Opaque: Standard Colour shades with medium to good opacity.
- Process Inks: „180“ colours 4 transparent colour shades according to Europe scale.
- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

### CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of TP 218/GL ink range contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish. Due to the binders (epoxy resin) pad printing inks TP 218/GL are not weather resistant. They are suitable for indoor and short-term outdoor applications.

### ADJUSTMENT FOR PAD PRINTING

- Pad printing inks TP 218/GL are not supplied in a ready-to-print adjustment.
- As this ink range is a 2-component system TP 218/GL inks have to be mixed with hardener at a specified ratio prior to processing.
- Thinner is added after addition of hardener.
- The mixed ink should be allowed to pre-react for approx. 15 minutes prior to processing (recommendation).
- Processing is then possible for a specified period of time (=pot life).

**Hardener:****Pad printing inks TP 218/GL are mixed with hardener 20 : 1 (parts by weight ink : hardener).**

For inks with none or low pigmentation hardener addition can be increased up to 10:1 to improve resistances.

The following hardeners are available:

- TP 219/GL** Good water resistance, limited solvent resistance.  
Recommended when only air drying (> 20°C), and oven-curing is not possible
- TP 219/02-GL** Recommended, when oven curing 140°C/ 20 – 30 minutes is possible.  
Prints will show good water resistance and quite a good solvent resistance.  
This hardener tends to yellowing and is therefore not recommended for light colours and bronzes.
- TP 219/03-GL** For air (> 20°C) and oven curing 140°C/20 – 30 minutes.  
Very good water and chemical resistance.  
Preferred for metal/chromium surfaces.

Hardeners are sensitive to humidity. Therefore, containers always have to be tightly closed.

**Pot life:**

- Ink mixed with hardener may only be processed within a limited period of time (=pot life)
- **Pot life of TP 218/GL + hardeners is approx. 8 h (at 20°C).**  
Higher temperatures will reduce pot life.
- We do not recommend processing the inks for longer than the pot life as adhesion and resistance properties will then continually deteriorate, even if the ink still seems to be liquid and processable.

**THINNERS / RETARDERS**

Depending on local conditions ink is adjusted to printing consistency by addition of 15 – 30 % by weight of thinner or retarder.

**Generally, the thinner suitable for TP 218/GL inks is Additive B!**

Depending on glass type and surface of the materials (e.g. contaminations) flow problems may occur. These can be improved with thinner VD10. Basically, however, substrates should be cleaned and degreased before printing. The additional products listed below should only be used if the required printing quality cannot be achieved using additive B (e.g. drying too slow or too fast).

For adjustment of pad inks TP 218/GL, the following products are available:

<b>Thinner:</b>	<input type="radio"/> Additive C	Extremely quick thinner, good solving power
	<input type="radio"/> VD 10	Very quick thinner, mild
	<input checked="" type="radio"/> <b>Additive B</b>	<b>Quick thinner, good solving power</b>
	<input type="radio"/> Additive A	Standard thinner
	<input type="radio"/> Additive U	Standard thinner, free of cyclohexanone
	<input type="radio"/> VD 60	Slow thinner
<b>Retarder:</b>	<input type="radio"/> TPD	Very slow retarder
■= Preferred    ○= If required		
<b>Note:</b>	<b>For printing with thick and thin steel clichés sensitive to corrosion</b>	
	<input type="radio"/> Additive A/00	Standard thinner with anti-corrosion additive
	<input type="radio"/> Additive B/00	Quick thinner with anti-corrosion additive

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients.

**ADDITIONAL AUXILIARY AGENTS**

<b>Application</b>	<b>Product</b>	<b>Addition in % by weight</b>	<b>Additional Information</b>
Antistatic paste	LAB-N 111420	Max. 10%	Possibly slightly reduced gloss
Retarder paste	LAB-N 111420/VP	Max. 10%	Possibly slightly reduced gloss
Viscosity increase	Thickening powder	Max. 3%	Stir with mixer
Matting	Matting powder	Max. 5%	Stir with mixer
Flow agent	VM 3	1 - 5%	Do not overdose!

**OVERPRINTING**

Generally, it is not necessary to overprint TP 218/GL inks with varnish. However, overprinting to achieve an enhanced protection of ink layers is possible with TP 218/GL-E50. Overprinting should be carried out within <12 hours.

**BRONZE COLOURS, MIXING OF BRONZE INKS**

Bronze colours are available upon request.

Printers can mix bronzes themselves using bronze pastes B 75 to B 79.

For examples of colour shades please refer to our Bronze Colour Card.

These "B" bronze pastes are mixed with bronze binder TP 218/B-GL or varnish TP 218/GL-E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste to TP 218/B-GL or TP 218/GL-E50 = 1 : 3 - 4

Silver bronze paste to TP 218/B-GL or TP 218/GL-E50 = 1 : 4 - 5

Contrary to AB and MG bronze colours, B bronzes tend to oxidation. Therefore they should be overprinted, e.g. with TP 218/GL-E50.

Note: When overprinting bronze colours (B/ AB/ MG) with varnish or other colour shades it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test).

Overprinting should be carried out within <12 hours.

**DRYING / HARDENER REACTION**

Mixture of TP 218/GL ink/hardener is a chemically-reactive system with a physical pre-drying.

- Ink dries physically by evaporation of solvents.
- Then the ink film cures by chemical cross-linkage reaction.
- **Drying and reaction temperature of hardener must be at least 20°C for all three types of above-mentioned TP 219/GL hardeners!**

**Drying**

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer (single print, multi-layer print).
- Drying temperature.

Drying time is approx. 10 – 15 minutes at room temperature (20 – 25°). Drying time with heat application (e.g. hot air fan) and air circulation is about 40 - 60 seconds.

Complete drying may take up to several hours, also depending on the substrate.

**Hardener Reaction**

Basically, the increased resistance properties of the printed ink film are only achieved after complete drying followed by chemical cross linkage reaction between ink and hardener. This cross linkage reaction depends on time and temperature. Until fully cured the minimum temperatures should not fall below 20°C. In addition, avoid high humidity.

Cross-linkage reaction will be much quicker using higher temperatures.

The following are guide values only:

Temperature	Time approx.	Condition of ink	Additional information
<20°C air drying		Hardeners TP 219/GL, TP 219/02-GL or TP 219/03-GL do not react!	Ink film will not achieve any resistance
20°C air drying	20 min.	"touch-dry"	No resistance yet
	<12 h	Still good overprintability	No resistance yet
	>72 h	High degree of cross-linkage	High resistances achieved
	>5 days	Maximum degree of cross-linkage	Maximum resistances achieved
80°C oven curing	approx. 5 min.	Dry enough for overprinting	No resistance yet
	60 min.	High degree of cross-linkage	High resistance values achieved
140° oven curing	30 min.	Maximum degree of cross-linkage	Maximum resistance values achieved

### Resistance Tests

Resistances should not be checked before the ink has fully cured/cross-linked:

Drying with 20°C/5 days; 80°C/>60 minutes\* 140°C/30 minutes\*

\*After oven curing allow a cooling time (room temperature 20°C) of at least 1h.

### CLICHÉ

All commercial types of clichés (polymer, thin and thick steel, ceramic) are suitable for processing TP 218/GL inks.

Note: Standard shades 65, 65-HD, 17, 50 and 51 cannot be used for closed ink systems with a magnet holder as they contain pigments with iron oxide content.

### CLEANING

The longer inks dry on clichés, pots and tools the harder will be their removal due to the chemical cross-linkage reaction. Therefore, always remove ink residues as soon as possible using our universal cleaning agents URS, URS 3 or thinner VD 40.

### PACK SIZE

Pad printing inks TP 218/GL are delivered in 1 litre containers. Other pack sizes are available upon request.

### SHELF LIFE

In closed original containers, TP 218/GL inks generally have a shelf life of 5 years from date of production. Hardeners TP 219/GL, TP 219/02-GL and TP 219/03-GL have a shelf life of 2 years from date of production, also in closed original containers.

For exact date of expiry, please refer to the label.

### SAFETY DATA SHEETS

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

### CLASSIFICATION AND LABELLING

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

### CONFORMITY

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy. Pad printing inks range TP 218/GL C-MIX 2000 colour shades, standard, highly opaque standard colours (HD), process colours, silver, fluorescent colours and transparent colours comply with the requirements of toy standard „EN 71-3:2019 Safety of toys – Migration of certain elements (category III: scraped off material).

Further compliance confirmations are available upon request.

### ADDITIONAL INFORMATION ABOUT OUR PRODUCTS

Product data sheets: Auxiliary Agents for Pad Printing HM

Brochures: Pad Printing Inks

Internet: Various technical articles are available for download on [www.coates.de](http://www.coates.de), section "SN-Online"; e.g. "Processing of 2-component Inks"

**FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.**

**COLOUR SHADES**

<b>C-MIX 2000 BASE COLOUR SHADES</b>			
<b>Mixing system for matching of PMS, HKS, RAL colours (on white substrates)</b>			
Start formulations available in data base „Formula Management C-MIX 2000“			
<b>According to colour card C-MIX 2000</b>			
primrose	TP 218/GL-Y30	red	TP 218/GL-R50
golden yellow	TP 218/GL-Y50	magenta	TP 218/GL-M50
orange	TP 218/GL-O50	violet	TP 218/GL-V50
scarlet	TP 218/GL-R20	blue	TP 218/GL-B50
green	TP 218/GL-G50	black	TP 218/GL-N50
white	TP 218/GL-W50	varnish	TP 218/GL-E50
<b>STANDARD (medium opacity)</b>			
<b>According to colour card STANDARD 2 for pad printing inks or TP 218/ TP 300...</b>			
Availability of further standard shades upon request			
citric yellow	TP 218/10-GL-NT	ultra marine	TP 218/32-GL-NT
medium yellow	TP 218/11-GL-NT	dark blue	TP 218/33-GL-NT
dark yellow	TP 218/12-GL-NT	violet	TP 218/37-GL-NT
orange	TP 218/15-GL-NT	light green	TP 218/40-GL-NT
light red	TP 218/20-GL-NT	fir green	TP 218/41-GL-NT
bright red	TP 218/21-GL-NT	brilliant green	TP 218/42-GL-NT
carmine red	TP 218/22-GL-NT	light brown	TP 218/50-GL-NT
pink	TP 218/25-GL-NT	dark brown	TP 218/51-GL-NT
light blue	TP 218/30-GL-NT	white	TP 218/60-GL-NT
medium blue	TP 218/31-GL-NT	black	TP 218/65-GL-NT
<b>STANDARD Colour Range HD (high opacity)</b>			
<b>According to colour card STANDARD HD for pad printing inks</b>			
Availability of further standard HD shades upon request			
white, highly opaque	TP 218/60-GL-HD-NT	black, highly opaque	TP 218/65-GL-HD-NT
<b>SPECIAL PRODUCTS: Special Colour Shades, Varnishes, Pastes</b>			
Information about availability upon request			
white, matt	TP 218/60-GL-MT-NT	transparent paste	TP 218/TP-GL
black, matt	TP 218/65-GL-MT-NT	bronze binder	TP 218/B-GL-NT
<b>4 COLOUR PROCESS INKS (CMYK)</b>			
<b>According to colour card STANDARD 2 for pad printing inks or TP 218/ TP 300...</b>			
process yellow	TP 218/180-GL-NT	process black	TP 218/65-GL-NT
process magenta	TP 218/181-GL-NT	transparent paste	TP 218/TP-GL
process cyan	TP 218/182-GL-NT		TP 218/GL-E50
<b>AB – BRONZE INKS and MG – METAL GLOSS INKS</b>			
<b>According to Bronze Colour Card</b>			
<b>AB Bronze Inks</b>		<b>MG Metal Gloss Inks</b>	
<b>Upon request</b>		<b>Upon request</b>	

Matching of PMS, RAL, NCS colours and special shades upon request.

*The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.*

*All former product data sheets are no longer valid.*

January 2020 - Version B3

**Coates Screen Inks GmbH**  
 Wiederholdplatz 1 90451 Nürnberg  
 Tel.: 0911 6422 0 Fax: 0911 6422 200  
<http://www.coates.de>